



### SE 30 Fill Sand Grading Results

Project:  
 Location:  
 Customer:  
 Track #:

Sieve	Wt. Ret.	% Ret.	% Pass.		
#4 (4.75mm)	39	8	92		
#8 (2.36mm)	93	18	82		
#16 (1.18mm)	154	30	70		
#30 (600um)	235	45	55		
#50 (300um)	342	66	34		
#100 (150um)	413	80	20		
#200 (75um)	443	85	15		
Pan	519	S.E. 35			

