



### Type 3 Aggregate Slurry Grading Results

Project:

Location:

Customer:

Track #:

Sieve	Wt. Ret.	% Ret.	% Pass.	Low Lim.	Upp. Lim.
3/8" (9.5mm)	0	0	100	100	100
#4 (4.75mm)	223	23	77	70	90
#8 (2.36mm)	391	40	60	45	70
#16 (1.18mm)	548	56	44	28	50
#30 (600um)	671	68	32	19	34
#200 (75um)	914	93	7	5	15
Pan	980	S.E. N/A		Moisture 2%	

