



1" Crushed Agg. Grading Results

Project:
 Location:
 Customer:
 Track #:

Sieve	Wt. Ret.	% Ret.	% Pass.	Low Lim.	Upp. Lim.
2" (50.0mm)	0	0	100	100	100
1" (25.0mm)	85	8	92	90	100
3/4" (19.0mm)	561	55	45	30	60
3/8" (9.5mm)	945	93	7	0	20
#4 (4.75mm)	989	97	3	0	5
Pan	1018				

Grading Limits Are In Accordance With Sec. 200-1.2 Of The Public Works "Green Book"

