



1/2" Crushed Agg. Grading Results

Project:
 Location:
 Customer:
 Track #:

Sieve	Wt. Ret.	% Ret.	% Pass.	Low Lim.	Upp. Lim.
3/4" (19.0mm)	0	0	100	100	100
1/2" (12.5mm)	113	2	98	90	100
3/8" (9.5mm)	3549	71	29	20	60
#4 (4.75mm)	4691	94	6	0	15
#8 (2.36mm)	4952	99	1	0	5
Pan	5014				

Grading Limits Are In Accordance With Sec. 200-1.2 Of The Public Works "Green Book"

CT 211 L.A. Rattler 100 revs 7.4% Loss

500 revs 30.8 % Loss

