



3/4" Crushed Agg. Grading Results

Project:
 Location:
 Customer:
 Track #:

Sieve	Wt. Ret.	% Ret.	% Pass.	Low Lim.	Upp. Lim.
1" (25.0mm)	0	0	100	100	100
3/4" (19.0mm)	140	3	97	90	100
1/2" (12.5mm)	2785	52	48	30	60
3/8" (9.5mm)	4705	88	12	0	20
#4 (4.75mm)	5268	99	1	0	5
Pan	5338				

Grading Limits Are In Accordance With Sec. 200-1.2 Of The Public Works "Green Book"

