



### 3/8" Crushed Agg. Grading Results

Project:  
 Location:  
 Customer:  
 Track #:

| Sieve         | Wt. Ret. | % Ret. | % Pass. | Low Lim. | Upp. Lim. |
|---------------|----------|--------|---------|----------|-----------|
| 1/2" (12.5mm) | 0        | 0      | 100     | 100      | 100       |
| 3/8" (9.5mm)  | 11       | 1      | 99      | 90       | 100       |
| #4 (4.75mm)   | 1035     | 68     | 32      | 30       | 60        |
| #8 (2.36mm)   | 1468     | 96     | 4       | 0        | 10        |
| Pan           | 1533     |        |         |          |           |

Grading Limits Are In Accordance With Sec. 200-1.2 Of The Public Works "Green Book"

