



Plaster Sand Grading Results

Project:
 Location:
 Customer:
 Track #:

Sieve	Wt. Ret.	% Ret.	% Pass.	Low Lim.	Upp. Lim.
#4 (4.75mm)	0	0	100	100	100
#8 (2.36mm)	5	1.1	99	95	100
#16 (1.18mm)	61	14	86	70	95
#30 (600um)	174	39	61	35	70
#50 (300um)	312	69	31	5	35
#100 (150um)	411	91	9	0	10
#200 (75um)	444	99	1	0	5
Pan	450	S.E. 85			

Grading Limits Are In Accordance With Sec. 200-1.5.4 Of The Public Works "Green Book"

